

RENOLIT ALKORPLAN D 35x76-101

Walkway membrane



SQUAD.BE

Product information

RENOLIT ALKORPLAN D 35x76
Synthetic roofing membrane of flexible PVC with polyester scrim reinforcing and an embossed top layer.

Certificates

Product certification EN 13956
0749-CPR-BC2-320-01452-0001-01

Certificates available on our website
www.renolit.com/roofing

Application

Walkway membrane for delineating maintenance, access and emergency routes.

PRODUCT DATA			
	Method	Production values	Unit
		RENOLIT ALKORPLAN D 35x76-101	
		1.5 mm	
Mass per unit area	EN 1849-2	1.85	kg/m ²
Tensile strength	EN 12311-2 (A)	≥1100	N/50 mm
Elongation	EN 12311-2 (A)	≥16	%
Dimensional stability (6h at 80 °C)	EN 1107-2	≤0.3	%
Foldability at low temperature	EN 495-5	≤-25	°C
Nail tear resistance	EN 12310-1	≥400	N
Tear resistance	EN 12310-2	≥225	N
Joint peel resistance	EN 12316-2	BOJ or ≥225	N/50 mm
Water vapour diffusion resistance (μ)	EN 1931	20,000	-
Resistance to static perforation	EN 12730	≥20	kg
External fire performance	EN 13501-5	NPD	-
Reaction to fire	EN 13501-1	E	-

PACKAGING					
	Colour	Thickness	Width	Roll length	Roll weight
RENOLIT ALKORPLAN D 35x76-101	Charcoal (79851)	1.5 mm	0.80 m	15 lm	ca. 15 kg

Storage

The rolls should be stored horizontally and parallel to each other. Store in the original packaging, in a dry and frost-free area, protected from direct sunlight. The maximum stack height in the original pallet packaging is 3 high with a protection between the pallets.

The **RENOLIT ALKORPLAN** roofing membranes are supplied in rolls on cardboard cores. Every delivery may contain up to 10% of short rolls (minimum length: 8 m).

This document replaces and supersedes all prior versions.

WWW.RENOLIT.COM/ROOFING

RENOLIT Cramlington Ltd, Station Road - Cramlington, Northumberland NE23 8AQ - United Kingdom
T +44 1670 718283 - F +44 1670 719367 - renolit.cramlington@renolit.com
RENOLIT Belgium N.V. - Export Dpt. - Industriepark De Bruwaan 43 - 9700 Oudenaarde - Belgium
T +32 (0)55 33 98 51 - F +32 (0)55 31 86 58 - renolit.belgium@renolit.com



R2.X7.6EX0.323